



FLEXLINER: POLYVINYLCHLORIDE COATED FELT (PVC)

PRODUCT DESCRIPTION

Polyester fibre flexible Liner with Polyvinylchloride coating custom sized for pipe rehabilitation manufactured in accordance with ISO 9001:2015. To accommodate the requirement for liners of varying thicknesses multi-layer liners are employed using multiple polyester fibre rolls.

DIMENSION AVAILABILITY

| | HOT CURE EVERSION | AMBIENT/WARM CURE EVERSION | HOT CURE DRAG-IN | AMBIENT/WARM CURE DRAG-IN |
|----------------|--|----------------------------|------------------|---------------------------|
| DIAMETER | 100mm to 300mm | 70mm to 300mm | 100mm to 300mm | 70mm to 300mm |
| THICKNESS | 3mm to 4.5mm | 3mm to 4.5mm | 3mm to 4.5mm | 3mm to 4.5mm |
| LENGTH | Up to 250m | Up to 250m | Up to 250m | Up to 250m |
| COATING WEIGHT | 400GSM (NOMINAL) | | | |
| LINER DESIGN | Liner undersized <10% | | | |
| | Liner features a welded or stitched seam. Stitched liners only available up to 300mm diameter. | | | |
| | Liner can negotiate pipe bends up to 45° | | | |

INSTALLATION METHODS

| LINER TYPE | RESIN TYPE | | CURING REGIME | | | | |
|----------------------------|------------|-------------------------|-----------------|-------------|---------|------------------|----------------------|
| | EPOXY | POLYESTER / VINYL ESTER | HOT WATER <90°C | STEAM <90°C | AMBIENT | WARM WATER <50°C | WARM AIR ACCELERATED |
| HOT CURE EVERSION | ✓ | ✗ | ✓ | ✓ | ✓ | ✓ | ✓ |
| AMBIENT/WARM CURE EVERSION | ✓ | ✓ | ✗ | ✗ | ✓ | ✓ | ✓ |
| HOT CURE DRAG-IN | ✓ | ✗ | ✓ | ✓ | ✓ | ✓ | ✓ |
| AMBIENT/WARM CURE DRAG-IN | ✓ | ✓ | ✗ | ✗ | ✓ | ✓ | ✓ |

TEST SPECIFICATIONS

| ROLL | CHARACTERISTIC | TEST | STANDARD |
|------|--|--|----------|
| | Density, Gauge of liner under various applied pressures. | Compression test of sample of all layers. | ISO 845 |
| | Felt weld strengths. | Each weld is sampled and destructively tested. | ISO 1421 |
| | Sealing tape weld strengths. | Each weld is sampled and destructively tested. | ISO 1421 |

Note: Liners are manufactured to internal standard or customer specifications. All liners are tested to the tests declared above and adhere to the declared ISO standards. Test data is available on request.

We recommend that all supplied Liners are supported sufficiently to avoid both Radial and Axial Expansion. We also recommend the use of Formed Stop ends when possible in Reception Manholes or Access Pits.





FLEXLINER: POLYVINYLCHLORIDE COATED FELT (PVC)

PRODUCT DESCRIPTION

| DIAMETER (mm) | LINER THICKNESS (mm) | EVERSION PRESSURE (bar) | MAX EVERSION PRESSURE (bar) | CURING PRESSURE (bar) | MAX PRESSURE (bar) @ 90°C | RESIN AMOUNT (Litre/m) | PINCH ROLLER GAP (mm) |
|---------------|----------------------|-------------------------|-----------------------------|-----------------------|---------------------------|------------------------|-----------------------|
| 70 | 3 | 0.86 | 1.32 | 0.86 | 1.15 | 0.6 | 8.5 |
| 100 | 3 | 0.60 | 0.92 | 0.60 | 0.81 | 0.8 | 8.0 |
| 125 | 3 | 0.48 | 0.74 | 0.48 | 0.65 | 1.1 | 8.0 |
| 150 | 3 | 0.40 | 0.62 | 0.40 | 0.54 | 1.3 | 8.0 |
| 150 | 4.5 | 0.60 | 0.92 | 0.60 | 0.81 | 1.9 | 12.0 |
| 200 | 3 | 0.30 | 0.46 | 0.30 | 0.40 | 1.7 | 8.0 |
| 200 | 4.5 | 0.45 | 0.69 | 0.45 | 0.61 | 2.6 | 11.5 |
| 225 | 3 | 0.27 | 0.41 | 0.27 | 0.36 | 2.0 | 8.0 |
| 225 | 4.5 | 0.40 | 0.62 | 0.40 | 0.54 | 2.9 | 11.5 |
| 250 | 3 | 0.24 | 0.37 | 0.24 | 0.32 | 2.2 | 8.0 |
| 250 | 4.5 | 0.36 | 0.55 | 0.36 | 0.48 | 3.2 | 11.5 |
| 275 | 3 | 0.22 | 0.34 | 0.22 | 0.29 | 2.4 | 8.0 |
| 275 | 4.5 | 0.33 | 0.50 | 0.33 | 0.44 | 3.5 | 11.5 |
| 300 | 3 | 0.20 | 0.31 | 0.20 | 0.27 | 2.6 | 8.0 |
| 300 | 4.5 | 0.30 | 0.46 | 0.30 | 0.40 | 3.9 | 11.5 |

1. Suitable only for Applied Felts liners designed for and to be installed by eversion.
2. Roller gap setting is for guidance only. Impregnation equipment differs: Rubber wrappings on rollers, positional hysteresis and flexing of rollers cause roller gap settings to vary between different equipment. Roller gap setting for any given equipment should be reasonably repeatable.
3. We strongly recommend the resin addition be monitored and controlled by adjustment of the roller gap setting. Ultimately, it is the correct resin addition which is imperative, not the roller gap.
4. All information is provided by Applied Felts in good faith, but without warranty. All calculations should be verified.



Contact Details